

TEST REPORT

2024AN0482

DATE OF RECEPTION

Date Format: dd/MM/yyyy 22/02/2024

DATE TESTS

Starting: 23/02/2024

Ending: 29/02/2024

APPLICANT

GABRIEL A/S
HJULMAGERVEJ, 55
DK-9000 Ålborg
Denmark

Att. BENTE ELLINGSOE

IDENTIFICATION AND DESCRIPTION OF SAMPLES

Reference by AITEX	Reference by customer	AITEX sample description
2024AN0482-S01	Art Contour 60360 Light Grey	Fabric
2024AN0482-S02	Art Contour 61304 Light Beige	Fabric
2024AN0482-S03	Art Contour 62150 Yellow	Fabric
2024AN0482-S04	Art Contour 63145 Light Orange	Fabric
2024AN0482-S05	Art Contour 64283 Red	Fabric
2024AN0482-S06	Art Contour 66275 Blue	Fabric
2024AN0482-S07	Art Contour 66276 Light Blue	Fabric
2024AN0482-S08	Art Contour 68317 Green	Fabric
2024AN0482-S09	Art Contour 68311 Dark Green	Fabric
2024AN0482-S10	Art Contour 68314 Light Green	Fabric

TESTS CARRIED OUT

- COLOUR FASTNESS TO RUBBING.

Tests marked with * are not included within the scope of the ENAC accreditation.

Rev.1 This revision cancels and replaces the previous





RESULTS

COLOUR FASTNESS TO RUBBING

Standard

ISO 105-X12:2016

Apparatus

Crockmeter

Starting test date

23/02/2024

Ending test date

29/02/2024

Conditioning time

> 4 H

Atmosphere for conditioning and testing

Temperature	(20±2) °C
Relative Humidity	(65±2) %Hr

Pin

Cylindrical

Applied force

(9 ± 0,2) N

% of water absorption for rubbing in humid

95-100 %

REFERENCE	DIRECTION	DRY STAINING	WET STAINING
2024AN0482-S01	Warp	5	5
	Weft	5	4-5
2024AN0482-S02	Warp	5	5
	Weft	5	4-5
2024AN0482-S03	Warp	5	4-5
	Weft	5	4-5
2024AN0482-S04	Warp	5	5
	Weft	5	5
2024AN0482-S05	Warp	4-5	4-5
	Weft	4-5	4-5
2024AN0482-S06	Warp	4-5	4-5
	Weft	4-5	4-5
2024AN0482-S07	Warp	5	5
	Weft	5	5
2024AN0482-S08	Warp	5	4-5
	Weft	5	4-5
2024AN0482-S09	Warp	4-5	4-5
	Weft	4-5	4-5
2024AN0482-S10	Warp	4-5	5
	Weft	5	4-5





REFERENCE	DIRECTION	CHANGUE IN COLOUR DRY	CHANGUE IN COLOUR WET
2024AN0482-S01	Warp	5	5
	Weft	5	5
2024AN0482-S02	Warp	5	5
	Weft	5	5
2024AN0482-S03	Warp	5	5
	Weft	5	5
2024AN0482-S04	Warp	5	5
	Weft	5	5
2024AN0482-S05	Warp	5	5
	Weft	5	5
2024AN0482-S06	Warp	5	5
	Weft	5	5
2024AN0482-S07	Warp	5	5
	Weft	5	5
2024AN0482-S08	Warp	5	5
	Weft	5	5
2024AN0482-S09	Warp	5	5
	Weft	5	5
2024AN0482-S10	Warp	5	5
	Weft	5	5

///

The test was carried out at laboratory located at Carretera Banyeres s/n - 03802 Alcoi, Alicante

Reference	Description
2024AN0482-S01	Art Contour 60360 Light Grey
2024AN0482-S02	Art Contour 61304 Light Beige
2024AN0482-S03	Art Contour 62150 Yellow
2024AN0482-S04	Art Contour 63145 Light Orange
2024AN0482-S05	Art Contour 64283 Red
2024AN0482-S06	Art Contour 66275 Blue
2024AN0482-S07	Art Contour 66276 Light Blue
2024AN0482-S08	Art Contour 68317 Green
2024AN0482-S09	Art Contour 68311 Dark Green
2024AN0482-S10	Art Contour 68314 Light Green



RESULTS

COLOUR FASTNESS TO RUBBING

Standard

AATCC TM 8:2016

Apparatus

Crockmeter

Starting test date

23/02/2024

Ending test date

29/02/2024

Scale used

AATCC Gray scale for staining (AATCC evaluation procedure 2)

Reference	Dry staining	Wet staining
2024AN0482-S01	4-5	4-5
2024AN0482-S02	4-5	4-5
2024AN0482-S03	5	5
2024AN0482-S04	4-5	5
2024AN0482-S05	4-5	4-5
2024AN0482-S06	4-5	4-5
2024AN0482-S07	5	5
2024AN0482-S08	5	4-5
2024AN0482-S09	4-5	4-5
2024AN0482-S10	5	5

///

The test was carried out at laboratory located at Carretera Banyeres s/n - 03802 Alcoi, Alicante

Reference	Description
2024AN0482-S01	Art Contour 60360 Light Grey
2024AN0482-S02	Art Contour 61304 Light Beige
2024AN0482-S03	Art Contour 62150 Yellow
2024AN0482-S04	Art Contour 63145 Light Orange
2024AN0482-S05	Art Contour 64283 Red
2024AN0482-S06	Art Contour 66275 Blue
2024AN0482-S07	Art Contour 66276 Light Blue
2024AN0482-S08	Art Contour 68317 Green
2024AN0482-S09	Art Contour 68311 Dark Green
2024AN0482-S10	Art Contour 68314 Light Green

**MEANING OF COLOUR FASTNESS APPRAISAL EVALUATED WITH GREY SCALE**

VALUE	MEANING
5	VERY GOOD - EXCELLENT
4	GOOD
3	FAIR - MODERATE
2	POOR - BEHAVIOUR
1	VERY POOR

According to standards ISO 105-A02 e ISO 105-A03



Date: 04/03/2024 14:37:58

Digitally Signed by: MARIA ISABEL SORIANO SARRIO -

NIF: 52716426N

LIABILITY CLAUSES

- 1.- AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2.- AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document. AITEX laboratories do not carry out sampling.
- 3.- The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4.- In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5.- AITEX will provide at the request of the person concerned, the treatment of complaints procedure. In the event that you want to make it, direct it to: calidad@aitex.es.
- 6.- AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results.
- 7.- AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8.- AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9.- When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule according to ILAC-G8: 2009 will be applied with a security zone of 1U and a Probability of False Acceptance <2.5%.
- 10.- The uncertainties of tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (95% probability of coverage). If not informed, they are available to the client in AITEX.
- 11.- The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 12.- This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13.- The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14.- The client must attend at all times, to the dates of the realization of the tests.
- 15.- According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16.- This report may not be partially reproduced without the written approval of the issuing laboratory.
- 17.- The tests have been carried out at the Alcoy plant with the address described on the first page of the report, unless another location is indicated in the results sheet of the specific test.