

Softlines

<b>Test Report</b>	No. 28511302	Date: 15 <sup>th</sup> February 2021	Page 1 of 3
--------------------	--------------	--------------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:


<b>Sample Description</b>	:	Europost
<b>Customer</b>	:	<b>Gabriel</b>
<b>Colour</b>	:	61107
<b>Product type</b>	:	Upholstery fabric
<b>Fiber content</b>	:	-

Test Performed \* : Selected test(s) as requested by applicant  
 Sample Receiving Date : 11<sup>th</sup> January 2021  
 Testing Period : 11<sup>th</sup> January 2021 – 15<sup>th</sup> February 2021  
 Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property	Results
Abrasion	-
Colour fastness to Water Spotting	-
Colour Fastness to Rubbing (Wet & Dry)	-
Seam Slippage	-

Signed for and on behalf of  
TÜV Rheinland UK LTD

George  
Mehmet  
  
2021.02.11  
10:20:28 Z

**George Mehmet**  
**Laboratory Technician**



8400

*Test result is drawn according to the kind and extent of tests performed.  
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

<b>Test Report</b>	No. 28511302	Date: 15 <sup>th</sup> February 2021	Page 2 of 3
--------------------	--------------	--------------------------------------	-------------

**Results:**

<b>Abrasion Resistance</b> (BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)			
<b>Result</b>			
	<b>Specimen 1</b>	<b>Specimen 2</b>	<b>Specimen 3</b>
End point reached, No three thread breakdown	50,000	50,000	50,000
Overall result	50,000		
Colour Change At 3000 (rubs)	5	5	5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

<b>Colour Fastness To Rubbing</b> (BS EN ISO105-X12:2016); Size of rubbing finger: 16mm diameter			
<b>Staining</b>		<b>Colour Change</b>	
Length	Width	Length	Width
Dry: 5 Wet: 5	Dry: 5 Wet: 5	Dry: 5 Wet: 5	Dry: 5 Wet: 5

**Note:** Colour change not a requirement of the standard, this was carried out at the request of the client

<b>Colour Fastness To Water Spotting*</b> (BS EN ISO 105-E07: 2010)	
<b>After 2 Minutes</b>	<b>Dry</b>
Grade: 3	Grade: 5

Tests indicated\* are non-UKAS accredited

<b>Seam Slippage</b> (BS EN ISO 13936-2:2004)	
<b>Sample</b>	<b>Result</b>
Warp	1.0(mm)
Weft	1.0(mm)

-End of Test Report-



**TÜVRheinland**<sup>®</sup>  
Precisely Right.

Softlines

**Gabriel**<sup>®</sup>

<b>Test Report</b>	<b>No. 28511302</b>	<b>Date: 15<sup>th</sup> February 2021</b>	<b>Page 3 of 3</b>
--------------------	---------------------	--	--------------------