



TEST REPORT

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 101373

Date received: 16/08/2018

Client's Description: 5 samples of fabric: Event Screen, Colours: 62048, 62093, 62095, 62096 & 68145

Test Required: Colour Fastness to Light & Colour Fastness to Rubbing

Date Tests Completed: 15/09/2018

Colour Fastness to Light: BS EN ISO 105-B02: 2014 Method 2

Specimens were exposed together with Standard References numbers 1-8. By comparison with the standard references the grading was found to be:

| | <u>BWS Rating</u> |
|-------|-------------------|
| 62048 | 6-7 |
| 62093 | 6 |
| 62095 | 7 |
| 62096 | 6 |
| 68145 | 6-7 |

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Vivienne Brockbank
Technician
15 September 2018

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104



Client: Gabriel

Entry No: 101373

Colour Fastness to Rubbing: BS EN ISO 105–X12: 2016^F

| <u>Staining</u> | | <u>Dry</u> | <u>Wet</u> |
|-------------------------|----------|------------|------------|
| 62048 | Warp Way | 5 | 5 |
| | Weft Way | 5 | 5 |
| 62093 | Warp Way | 5 | 5 |
| | Weft Way | 5 | 5 |
| 62095 | Warp Way | 5 | 4-5 |
| | Weft Way | 5 | 4-5 |
| 62096 | Warp Way | 5 | 5 |
| | Weft Way | 5 | 5 |
| 68145 | Warp Way | 5 | 5 |
| | Weft Way | 5 | 5 |
| <u>Change in Colour</u> | | <u>Dry</u> | <u>Wet</u> |
| All colours | Warp Way | 5 | 5 |
| | Weft Way | 5 | 5 |

Note: Change in colour is not a requirement of the method but was carried out at the request of the client.

-----End of Document-----