

Softlines

Test Report	No. 28511299	Date: 15 th February 2021	Page 1 of 3
--------------------	--------------	--------------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:


Sample Description	:	Gaja Classic
Customer	:	Gabriel
Colour	:	60019
Product type	:	Upholstery fabric
Fiber content	:	-

Test Performed * : Selected test(s) as requested by applicant *
 Sample Receiving Date : 11th January 2021
 Testing Period : 11th January 2021 – 15th February 2021
 Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Results
Colour Fastness to Rubbing (Wet & Dry)	-
Colour fastness to Water Spotting	-
Pilling	-
Colour Fastness to Lights	Sub-con within group results to follow on completion

Signed for and on behalf of
TÜV Rheinland UK LTD


George Mehmet
2021.02.11
10:26:34 Z

George Mehmet
Laboratory Technician



8400

*Test result is drawn according to the kind and extent of tests performed.
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

Test Report	No. 28511299	Date: 15 th February 2021	Page 2 of 3
--------------------	--------------	--------------------------------------	-------------

Results:

Colour Fastness To Rubbing (BS EN ISO105-X12:2016); Size of rubbing finger: 16mm diameter			
Staining		Colour Change	
Length	Width	Length	Width
Dry: 5 Wet: 5	Dry: 5 Wet: 5	Dry: 5 Wet: 5	Dry: 5 Wet: 5

Note: Colour change not a requirement of the standard, this was carried out at the request of the client

Pilling Resistance (BS EN ISO 12945-2:2000; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric) No cleansing required	
Sample	Average Result
After 2000 Rubs Rating	5
After 5000 Rubs Rating	5
Remarks: Pilling Rating 5 - No change 4 - Slight surface fuzzing and/or partially formed pills 3 - Moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen 2 - Distinct fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimen surface 1 - Dense surface and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface	

Colour Fastness To Water Spotting* (BS EN ISO 105-E07: 2010)	
After 2 Minutes	Dry
Grade: 4-5	Grade: 5

Tests indicated* are non-UKAS accredited

-End of Test Report-



TÜVRheinland[®]
Precisely Right.

Softlines

Gabriel[®]

Test Report	No. 28511299	Date: 15th February 2021	Page 3 of 3
--------------------	---------------------	--	--------------------