

Received: 01/17/2013	Completed: 02/04/2013	Letter: M	pp	P.O.#:	Test Report #:	2-95228-0-
Client's Identification: Task: 726. Article no.: 40-8613. Width: 140cm. Name: Medley. Composition: 100% Polyester. Colour: 61002 Beige.						
Tested For: Claus Johansen Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark					Key Test: ASTM E 84 (BLDG) 945 Tel: 011 45 3692 3137 Fax: 011 45 9811 6125 Ext:	

BLDG (IBC): LE 2012; R 06/12; V 6/12
ASTM E84: LE 2012; R 06/12; V 06/12

PC: ME /jd

TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials *

REFERENCE: Comparable to: UL 723 - Standard for Test for Surface Burning Characteristics of Building Materials

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.027"

PRODUCT CATEGORY:

- Textile Type Product
- Vinyl Type Product
- Other than Textile Type or Vinyl Type Product: _____

* Note: Textile or expanded vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or expanded vinyl wallcoverings are used in non-sprinklered areas, a room/corner fire test is mandated, such as NFPA 265 for textiles and NFPA 286 for expanded vinyls.

NFPA 286 test method standard applies not only to expanded vinyls, but also to all non-textile products. Therefore, it should be considered for all interior finish applications in non-sprinklered areas.

SPECIMEN MOUNTING:

- Self Supporting: The test specimen, the face of which was 23" ± 1" x 24', was such that it remained in position in the tunnel during the fire test, and no additional support was required.
- Adhered to IRC: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 23" ± 1" x 24'.
- Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board, to form a test specimen the face of which was 23" ± 1" x 24'.
- Unadhered: The 23" ± 1" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.
- Other: _____

Received:01/17/2013 Completed:02/04/2013 Letter: M pp P.O.#: Test Report #: 2-95228-0-

Client's Identification Task: 726. Article no.: 40-8613.Width:140cm. Name: Medley. Composition: 100% Polyester. Colour: 61002 Beige.

Tested For: **Claus Johansen** Key Test: ASTM E 84 (BLDG) 945
 Gabriel A/S
 Hjulmagervej 55 Tel: 011 45 3692 3137 Ext:
 DK-9000 Aalborg, Denmark Fax: 011 45 9811 6125

REMARKS: None.

RESULTS:
 Flame Spread Index: 5
 Smoke Developed: 55

CONCLUSION: Based on the above Results and Code Classification System the item tested is assigned a:
 Class I or A rating
 Class II or B rating
 Class III or C rating
 Unrated


DATA SUMMARY:
 Time to Ignition: 00.32 minutes
 Maximum Flame Spread "Distance": 00.96 feet
 Maximum Flame Spread "Time": 00.53 minutes

CODE CLASSIFICATION SYSTEM:

	Flame Spread Index	Smoke Developed
Class I or A:	0 - 25	450 or less
Class II or B:	26 - 75	450 or less
Class III or C:	76 - 200	450 or less

- BUILDING CODE CITATION FOR THE CLASSIFICATION SCHEME:
- (1) 2012 edition, NFPA 101 Life Safety Code, para. 10.2.3.4
 - (2) 2012 edition, NFPA 5000 Building Construction & Safety Code, para. 10.3.2
 - (3) 2012 edition, International Building Code, para. 803.1.1

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.

 FEB 07 2013

AUTHORIZED SIGNATURE
 THE GOVMARK ORGANIZATION, INC. CT /pm /96
MS. PHYLLIS PETTIT

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.