



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 15, 2022

Ms. Petra Kruecken
TREVIRA GmbH
Philipp-Reis-Straße 4
65795 Hattersheim
Germany

Reference: Flammability Test Report
Lab Identification No. 51872
Invoice No. 83157

Dear Ms. Kruecken:

One (1) fabric sample, identified as **Application No.: 220658; Article Name: Step/Step Melange; Color: 60090; Trademark: Trevira CS Woven Fabric for Drapes, Wallcovering and Curtains, Square Weight 335 g/m²; 100% Inherent Flame Retardant Polyester, 100% CS**, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Small-Flame Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame (sec)</u>		<u>Damaged Length (mm)</u>	
	<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>
1	0.0	0.0	91	89
2	0.0	0.0	95	91
3	0.0	0.0	104	87
4	0.0	0.0	76	91
5	0.0	0.0	100	90
Avg.			91	

The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

BSD/pd





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 15, 2022

Ms. Petra Kruecken
TREVIRA GmbH
Philipp-Reis-Straße 4
65795 Hattersheim
Germany

Reference: Flammability Test Report
Lab Identification No. 51872
Invoice No. 83157

Dear Ms. Kruecken:

One (1) fabric sample, identified as **Application No.: 220658; Article Name: Step/Step Melange; Color: 60090; Trademark: Trevira CS Woven Fabric for Drapes, Wallcovering and Curtains, Square Weight 335 g/m²; 100% Inherent Flame Retardant Polyester, 100% CS**, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Large-Flame Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame (sec)</u>	<u>Char Length (mm)</u>
Length 1	0.0	99
Length 2	0.0	101
Width 1	0.0	68
Width 2	0.0	49

The fabric sample submitted **meets** the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

BSD/mr

