

Received: 10/26/2018 **Completed:** 11/07/2018 **Letter:** C **RV** **P.O.#:** **Test Report #:** 3-29299-0-

Client's Identification Style: Tempt. Content: 100% Polyester. Finish: None. Weight: 504 g/lm. Color: 60900 Black. Product End Use: Upholstery.

Tested For: Bente Ellingsoe, Quality Department **Key Test:** ASTM D 5034/ACT 140
 Gabriel A/S
 Hjulmagervej 55 **Tel:** 011-45-9630-3100 **Ext:**
 DK-9000 Aalborg, Denmark **Fax:** 011-45-9811-6125

Test Category: Tensile Specifier: ACT LE 2015; V 08/15 PC: 8H dl/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA (for warp and weft):
-----	-----
<input checked="" type="checkbox"/> Upholstery	50 lbs. minimum average
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	35 lbs. minimum average
<input type="checkbox"/> Draperies	No requirement

RESULTS:

Direction	Specimen #	(lbs)
-----	-----	-----
Warp:	1	345
	2	283
	3	307
	4	344
	5	343
	Avg:	324
Weft:	1	193
	2	250
	3	229
	4	277
	5	282
	6	253
	7	194
	8	190
	Avg:	234


REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics

Received: 10/26/2018	Completed: 11/07/2018	Letter: C	RV	P.O.#:	Test Report #: 3-29299-0-
Client's Identification	Style: Tempt. Content: 100% Polyester. Finish: None. Weight: 504 g/lm. Color: 60900 Black. Product End Use: Upholstery.				
Tested For: Bente Ellingsoe, Quality Department	Key Test: ASTM D 5034/ACT			140	
Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark	Tel: 011-45-9630-3100		Ext:		
	Fax: 011-45-9811-6125				

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



Phyllis Pettit

 AUTHORIZED SIGNATURE
 SGS GOVMARK
 /jab /pm

NOV 15 2018

(Page 2 of 2)