



TEST REPORT

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 74379-01

Date received: 30/03/2016

Client's Description: 12 samples of fabric: Design 2472 Capture, 85/15 Wool/Polyamid, Colours: 4102, 4201, 4701, 4802, 4803, 4901, 5101, 5102, 5103, 5301, 5401, & 5402

Test Required: Colour Fastness to Light and Colour Fastness to Rubbing

Date Tests Completed: 04/05/2016

Colour Fastness to Light: BS EN ISO 105-B02: 2013 Method 2

Specimens were exposed together with Standard References numbers 1-8. By comparison with the standard references the grading was found to be:

	<u>BWS Rating</u>
4102	6
4201	5-6
4701	6
4802	5-6
4901	6
5101	6
5102	5-6
5103	5
5301	6
5401	7
5402	6-7

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank
Senior Technician
Date of original 04 May 2016
Date of amendment 12 May 2016

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104



Client: Gabriel
Entry No: 74379-01

Colour Fastness to Rubbing: BS EN ISO 105–X12:2002

<u>Staining</u>		<u>Dry</u>	<u>Wet</u>
4102	Warp Way	5	5
	Weft Way	5	5
4201	Warp Way	5	4-5
	Weft Way	5	4-5
4803	Warp Way	5	5
	Weft Way	5	5
4901	Warp Way	5	4-5
	Weft Way	5	4-5
5101	Warp Way	5	5
	Weft Way	5	5
5102	Warp Way	5	5
	Weft Way	5	4-5
5103	Warp Way	5	5
	Weft Way	5	5
5301	Warp Way	4-5	4-5
	Weft Way	4-5	4-5
<u>Change in Colour</u>		<u>Dry</u>	<u>Wet</u>
All colours	Warp Way	5	5
	Weft Way	5	5

Note: Change in colour is not a requirement of the method but was carried out at the request of the client.

-----End of Document-----