



Date of Issue: 1/4/2022
 Report Number: 21-006187
 Revision Number:1
 Date Order Received: 11/30/2021

For the Account of: Gabriel A/S
 Hjulmagervej 55
 9000 Aalborg Denmark

Client's Identification: Capture COL 4102

CERTIFICATE OF TESTING

TEST PERFORMED: Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Martindale Tester
 ASTM D4970/D4970M-16e2

TEST RESULTS

Specimen	Rating 1.5 in	Rating 5.5 in	
1	3.0	4.5	
2	3.0	4.5	
3	3.0	4.5	
4	3.0	4.5	
Average	3.0	4.5	Overall Average: 4.0

RATING SYSTEM

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

NOTES

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling Method:** As Received
- Viewing Apparatus:** SpectraLight QC Lightbooth
- Viewing Option:** 45 degree
- Rating Standard:** ADJD3512 Photographic Standards
- Running Times:** 1000 movements

ACCEPTANCE CRITERIA

- A.C.T. Standard:** Upholstery
- Acceptance Criteria:** Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 12/02/2021