



Date of Issue: 1/4/2022 Report Number: 21-006189

Revision Number:1

Date Order Received: 11/30/2021

For the Account of: Gabriel A/S

Hjulmagervej 55 9000 Aalborg Denmark

Client's Identification: GO UNI 60083

CERTIFICATE OF TESTING

TEST PERFORMED: Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Brush Pilling Tester ASTM D3511/D3511M-16

TEST RESULTS

	Rating
Left	5.0
Center	5.0
Right	5.0
Average Rating	5.0

RATING SYSTEM

Class 5.0 No Pilling
Class 4.0 Slight Pilling
Class 3.0 Moderate Pilling
Class 2.0 Severe Pilling
Class 1.0 Very Severe Pilling

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

Sampling Method: As Received
Viewing Apparatus: Macbeth Lightbooth

Viewing Option: 45 degree

Rating Standard: ADJD3512 Photographic Standards
Running Times: 4 minutes brushing / 2 minutes pilling

ACCEPTANCE CRITERIA

A.C.T. Standard: Acceptance Criteria
Upholstery Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1

Date Order Completed: 12/06/2021