



Received: 12/12/2017 | Completed: 12/13/2017 | Letter: H4 | RV | P.O.#: | Test Report #: 3-23625-4-

Client's Identification | Style: 2477 Felicity. Date of Mfg.: 28-11-2017. Composition: 100% Polyester. Weight: 432 g/lm. Product End Use: Upholstery. Color #: 67081.

Tested For: **Bente Ellingsoe, Quality Department** | Key Test: ASTM D 5034/ACT 140
 Gabriel A/S | Tel: 011-45-9630-3100 Ext:
 Hjulmagervej 55 | Fax: 011-45-9811-6125
 DK-9000 Aalborg, Denmark

Test Category: Tensile Specifier: ACT LE 2015; V 08/15 PC: 8H dl/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA (for warp and weft):
-----	-----
<input checked="" type="checkbox"/> Upholstery	50 lbs. minimum average
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	35 lbs. minimum average
<input type="checkbox"/> Draperies	No requirement

RESULTS:

Direction	Specimen #	(lbs)
-----	-----	-----
Warp:	1	236
	2	234
	3	227
	4	230
	5	239
	Avg:	233
Weft:	1	406
	2	400
	3	437
	4	370
	5	434
	6	439
	7	440
	8	347
	Avg:	409

REMARKS: None.


CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics



Received: 12/12/2017	Completed: 12/13/2017	Letter: H4	RV	P.O.#:	Test Report #:	3-23625-4-
Client's Identification	Style: 2477 Felicity. Date of Mfg.: 28-11-2017. Composition: 100% Polyester. Weight: 432 g/lm. Product End Use: Upholstery. Color #: 67081.					
Tested For: Bente Ellingsoe, Quality Department			Key Test: ASTM D 5034/ACT		140	
Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125		Ext:	

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



 AUTHORIZED SIGNATURE
 GOVMARK
 /rb /pm

Phyllis Pettit
 DEC 21 2017

(Page 2 of 2)