



Received:02/07/2018	Completed:02/14/2018	Letter: W2	TM	P.O.#:	Test Report #:	3-24458-2-
Client's Identification	Style: 2480 Cura. Date of Mfg.: 30-01-2018. Composition: 100% Post-Consumer Recycled Polyester. Weight: 420 g/lm. Color #: 60111-Black. Product End Use: Upholstery.					
Tested For:	Bente Ellingsoe, Quality Department		Key Test: ASTM D 3511/ACT		140	
	Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark		Tel: 011-45-9630-3100 Fax: 011-45-9811-6125		Ext:	

Test Category: Brush Pill Specifier: ACT LE 2015; V 08/15 PC: 4H d1/SM
 NTR 7/16

TEST PERFORMED: ASTM D 3511 - Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textiles Fabrics: Brush Pilling Tester Method (LE 2013; V 3/15) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery - Woven Fabrics

ACCEPTANCE CRITERIA: Class 3 Minimum Average

RESULTS:

Specimen #	Rating
1	Class 5
2	Class 5
3	Class 5

Avg:	Class 5

OBSERVATIONS:

Development of fuzzing observed: Yes; No
 Color change observed: Yes; No
 Loss of cover observed: Yes; No

REMARKS: None.

RATING SYSTEM:

- Class 5 - No pilling
- Class 4 - Slight pilling
- Class 3 - Moderate pilling
- Class 2 - Severe pilling
- Class 1 - Very severe pilling



Received:02/07/2018	Completed:02/14/2018	Letter: W2	TM	P.O.#:	Test Report #:	3-24458-2-
Client's Identification	Style: 2480 Cura. Date of Mfg.: 30-01-2018. Composition: 100% Post-Consumer Recycled Polyester. Weight: 420 g/lm. Color #: 60111-Black. Product End Use: Upholstery.					
Tested For:	Bente Ellingsoe, Quality Department	Key Test: ASTM D 3511/ACT			140	
	Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125	Ext:	

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Rhys Pettit

FEB 26 2018

 AUTHORIZED SIGNATURE

GOVMARK

/jb /pm

(Page 2 of 2)