



Received:05/04/2018	Completed:05/08/2018	Letter: P8	RV	P.O.#:	Test Report #:	3-25917-8-
Client's Identification	Style: Tonal. Content: 99% Post-Consumer Recycled Polyester, 1% Polyester. Finish: None. Weight: 318 g/lm. Color #: 60122. End Use: Upholstery. [Color as described by SGS Govmark: Light Grey]					
Tested For: Bente Ellingsoe, Quality Department	Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark				Key Test: AATCC 15	175
				Tel: 011-45-9630-3100	Ext:	
				Fax: 011-45-9811-6125		

LE: 2013; V 05/16

PC: NS

TEST PERFORMED: AATCC Test Method 15 - Colorfastness to Perspiration

RESULTS:

Rating  
 -----  
 Grade 5

1. Color change of sample --  
 Evaluated by comparison with:

AATCC Gray Scale for Color Change

2. Staining on multi-fiber #42 transfer cloth  
 (6 fiber wide band) --

Evaluated by comparison with:  
 AATCC Chromatic Transference Scale  
 AATCC Gray Scale for Staining

FIBER:	Acetate	Grade 5
	Cotton	Grade 5
	Nylon	Grade 5
	Polyester	Grade 5
	Acrylic	Grade 5
	Wool	Grade 5

NOTE: This test method is based on the use of an acid solution. Previous editions specified both acid and alkaline solutions. The alkaline solution has been eliminated from the test method.

REMARKS: None.


RATING SYSTEM:

- Grade 5 - No color change or transfer
- Grade 4 - Slight color change or transfer
- Grade 3 - Noticeable color change or transfer
- Grade 2 - Considerable color change or transfer
- Grade 1 - Severe color change or transfer

ACCEPTANCE CRITERIA: None cited.

CONCLUSION: Not applicable.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 -----  
 AUTHORIZED SIGNATURE

Phyllis Pettit

MAY 22 2018

SGS GOVMARK

/mg

(Page 1 of 1)