

Nepshaw Lane South, Morley, Leeds, LS277JQ Materials Testing Manager: Martin Bowden

t: 0113 5350176

e: Materials.Testing@wyjs.org.uk www.wyjs.org.uk/materialstesting



## **TEST REPORT**

Client: Gabriel

> Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

**Entry No:** 103323

Date received: 25/10/2018

Client's Description: 6 Fabric Samples Spin Dark Brown Grey 60021, Dark Yellow 62057, Red 64013,

Turquise 67007, Violet 65011, Yellow Green 68119.

**Test Required:** Colour Fastness to Light, Colour Fastness to Rubbing & Colour Fastness to Water

**Date Tests Completed:** 19/12/2018

Colour Fastness to Light: BS EN ISO 105-B02: 2014 Method 2

A specimen was exposed together with Standard References numbers 1-8. By comparison with the standard references the grading was found to be:

references the grading was round to be.	
	BWS Rating
Dark Brown Grey 60021	7
Dark Yellow 62057	7-8
Red 64013	7
Turquise 67007	7-8
Violet 65011	7-8
Yellow Green 68119	7-8

This is hereby certified to be a correct return of the tests made of the items referred to herein

Claire Saville Technologist

20th December 2018

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

- Tests marked <sup>N</sup> in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory. Tests marked <sup>F</sup> in this certificate are performed under the Laboratory's Flexible Scope of Accreditation. Tests marked <sup>S</sup> in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.









Client: Gabriel

**Entry No:** 103323



## Colour Fastness to Rubbing: BS EN ISO 105-X12: 2016F

		<u>Dry</u>	<u>Wet</u>
Dark Brown Grey 60021	Warp Way	5	5
	Weft Way	5	5
Dark Yellow 62057	Warp Way	5	5
	Weft Way	5	5
Red 64013	Warp Way	5	5
	Weft Way	5	5
Turquise 67007	Warp Way	5	5
	Weft Way	5	5
Violet 65011	Warp Way	5	5
	Weft Way	5	5
Yellow Green 68119	Warp Way	5	5
	Weft Way	5	5
Change in colour for all shades	Warp Way	5	5
-	Weft Way	5	5

This is not part of the standard but carried out at the request of the customer.

------End of Document------