

Received: 09/16/2019	Completed: 09/18/2019	Letter: X4	RV	P.O.#:	Test Report #: 3-34532-4-
Client's Identification	Style: Morph. Content: 85% New Zealand Wool / 15% Polyamide. Weight: 450 g/lm. Color: 11101 Light Orange. Product End Use: Upholstery.				
Tested For: Bente Ellingsoe, Quality Department				Key Test: ASTM D 5034/ACT	165
Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark				Tel: 011-45-9630-3100 Fax: 011-45-9811-6125	Ext:

Test Category: Tensile Specifier: ACT LE 2018; V 01/19 PC: 8H dl/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (August 2018)

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA (for warp and weft):
-----	-----
<input checked="" type="checkbox"/> Upholstery	50 lbs. minimum average
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	35 lbs. minimum average
<input type="checkbox"/> Draperies	No requirement

RESULTS:

Direction	Specimen #	(lbs)
-----	-----	-----
Warp:	1	153
	2	177
	3	176
	4	173
	5	181
	Avg:	172
Weft:	1	145
	2	143
	3	140
	4	154
	5	147
	6	147
	7	140
	8	148
	Avg:	146


REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics

Received: 09/16/2019	Completed: 09/18/2019	Letter: X4	RV	P.O.#:	Test Report #: 3-34532-4-
Client's Identification	Style: Morph. Content: 85% New Zealand Wool / 15% Polyamide. Weight: 450 g/lm. Color: 11101 Light Orange. Product End Use: Upholstery.				
Tested For: Bente Ellingsoe, Quality Department	Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark			Key Test: ASTM D 5034/ACT	165
			Tel: 011-45-9630-3100	Ext:	
			Fax: 011-45-9811-6125		

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



Phyllis Pettit

OCT 18 2019

 AUTHORIZED SIGNATURE
 SGS GOVMARK
 /ab /pm

(Page 2 of 2)