



Date of Issue: 3/17/2023  
 Report Number: 22-004222  
 Revision Number: 2  
 Date Order Received: 12/20/2022

For the Account of: Gabriel A/S  
 Hjulmagervej 55  
 9000 Aalborg Denmark

Client's Identification: Cubic col 61078

### CERTIFICATE OF TESTING

**TEST PERFORMED:** Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Brush Pilling Tester ASTM D3511/D3511M-16

**TEST RESULTS**

	Rating
Left	5.0
Center	5.0
Right	5.0
Average Rating	5.0

**RATING SYSTEM**

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

**NOTES**

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling Method:** As Received
- Viewing Apparatus:** Macbeth Lightbooth
- Viewing Option:** 45 degree
- Rating Standard:** ADJD3512 Photographic Standards
- Running Times:** 4 minutes brushing / 2 minutes pilling

**ACCEPTANCE CRITERIA**

- A.C.T. Standard:** Acceptance Criteria
- Upholstery Class 3 minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*Jillian Matice*  
**Jillian Matice**

Authorized Signature

Date Order Completed: 12/27/2022

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples as received under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the extent the sample tested is representative of the piece or lot.

Our reports and letters are for the exclusive use of the customer to whom they are addressed and they and the corporation named on the reverse are not to be used under any circumstances without prior written approval. Samples will not