

Gabriel[®]

Softlines

Test Report	No. 28512393	Date: 10 th March 2022	Page 1 of 2
-------------	--------------	-----------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description	:	Grain / Grain Melange Col: 63117	
Customer	:	Gabriel	
Product type	:	Upholstery fabric	
Content Fiber	:	-	

Test Performed : Selected test(s) as requested by applicant

Sample Receiving Date : 25th February 2022

Testing Period : 25th February 2022 – 10th March 2022

Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Remarks
Abrasion	•
Pilling	-

Signed for and on behalf of	
TÜV Rheinland UK LTD	

Dathan Stone 2022.03.10 15:58:02 Z

Dathan Stone Senior Laboratory Technician



8400

Test result is drawn according to the kind and extent of tests performed.

Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.



Gabriel'

Softlines

Test Report	No. 28512393	Date: 10 th March 2022	Page 2 of 2
-------------	--------------	-----------------------------------	-------------

Results:

Abrasion Resistance	ınce	ista	esi	R	on	sic	ra	۱b	Α
---------------------	------	------	-----	---	----	-----	----	----	---

(BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)

P	ACI	ы
	1251	V I

	Specimen 1	Specimen 2	Specimen 3
End point reached, no three thread breakdown	100,000	100,000	100,000
Colour Change At 3000 (rubs)	5	5	5

Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification

Pilling Resistance

(BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric)

No cleansing required

Deviation: At clients request - only pilling surface characteristics a	Average Result
After 2000 Rubs Rating	Pilling 5
After 5000 Rubs Rating	Pilling 5

-End of Test Report-