



Confidential Report

Our Ref: 23/58449-2





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 28 April 2021

Our Ref: 23/58449-2
Your Ref: ---

Page: 1 of 4

Client: **Gabriel A/S**
Hjulgagerve 55
DK-900 Aalborg
Denmark

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: 0011530517

Date of Receipt: 14 April 2021

Date Test Started: 22 April 2021

Description of Sample: One sample of fabric, which was referenced by the client as;
Item Description: Athlon 60140 Light Grey, Item Number: 650060140, stated to be 100% Polyester

Work Requested: We were asked to test the received sample to the following standard:
BS EN 1021:Part 1:2014 – Ignitability of Upholstered Furniture

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 28 April 2021

Our Ref: 23/58449-2
Your Ref: ---

Page: 2 of 4

Client: Gabriel A/S

FIRE TEST ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

Pre-Treatment

The sample did not have a flame retardant treatment therefore it was not subjected to a water soak pre-treatment

Conditioning

The sample was conditioned for at least 16 hours at a temperature of $23\pm 2^{\circ}\text{C}$ and relative humidity of $50\pm 5\%$.

The sample was tested in a room of volume 25m^3 and 17°C .

Procedure

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately $20\text{-}22\text{ kg/m}^3$.


Tests were made using ignition source 0.

Requirements

The specimens shall not:-

Smouldering Criteria

- display escalating combustion requiring active extinction.
- smoulder or burn until it is essentially consumed within the test duration.
- smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- smoulder for more than one hour.
- on final examination, show evidence of progressive smouldering.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: info@bttg.co.uk
 : www.bttg.co.uk

Date: 28 April 2021
 Our Ref: 23/58449-2
 Your Ref: ---
 Page: 3 of 4

Client: Gabriel A/S

Requirements (continued)

Flaming Criteria

- a) show evidence of flaming initiated by a smouldering source.

Results

	Specimen No.	
	1	2
Smouldering criteria	1	2
Placement of Cigarette	Flat	Flat
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Smoulders to extremities/full thickness	No	No
Smoulders more than 1 hour	No	No
In final examination, presence of progressive smouldering	No	No
Flaming criteria	1	2
Occurrence of flames	No	No
Specimen Result (Ignition or Non-ignition)	Ignition (I)	Ignition (I)

Any “Yes” in smouldering or flaming criteria means Ignition

Cigarette Test Result **PASS**

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
: www.bttg.co.uk

Date: 28 April 2021

Our Ref: 23/58449-2

Your Ref: ---

Page: 4 of 4

Client: **Gabriel A/S**

Comments


An NI designation indicates the sample meets the performance requirements of BS EN 1021-1.

This report relates only to the samples submitted and as described in the report.

The overall uncertainty budget for BS EN 1021:Part 1:2014 is as follows:-

Timings: ± 2 seconds.

Reported by:.....
B Bland
Technical Customer Service Officer

Countersigned By:.....
P Doherty
Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTG™ and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.