

# **Confidential Report**

Our Ref: 23/48848B/08/21





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

: www.bttg.co.uk

Date: 24 August 2021

Our Ref: 23/58848B/08/21

Your Ref: ---

Page: 1 of 6

Client: Gabriel A/S

Hjulmagerve 55 DK-900 Aalborg Denmark

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: 0011547263

Date of Receipt: 12 August 2021

Date Test Started: 24 August 2021

Description of Sample: One sample of fabric, which was referenced by the client as;

Blend 01102 Blue, Design No: 231601101

Work Requested: We were asked to test the received sample to the following standard:

BS EN 1021: Parts 1 & 2:2014 - Ignitability of Upholstered Furniture



\*\* subcontracted test, EN ISO/IEC 17025 accredited

\*\*\* not UKAS accredited



Note: This report relates only to the samples submitted and as described in the report.



Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 24 August 2021

Our Ref: 23/58848B/08/21 Your Ref: ---

Page: 2 of 6

Client: Gabriel A/S

## FIRE TEST ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

#### **Pre-Treatment**

The material received no pre-treatment as the fabric is stated not to be FR treated.

# **Conditioning**

The sample was conditioned for at least 16 hours at a temperature of  $23\pm2^{\circ}$ C and relative humidity of  $50\pm5\%$ .

The sample was tested in a room of volume 25m<sup>3</sup> and 20°C.

#### **Procedure**

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 35-36 kg/m<sup>3</sup>.

Tests were made using ignition source 0.

# Requirements

The specimens shall not:-

## **Smouldering Criteria**

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) on final examination, show evidence of progressive smouldering.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 24 August 2021

Our Ref: 23/58848B/08/21 Your Ref: ---

Page: 3 of 6

Client: Gabriel A/S

# Requirements (continued)

## Flaming Criteria

a) show evidence of flaming initiated by a smouldering source.

#### **Results**

| Smouldering criteria                                      | Specimen No. |      |  |
|---|--------------|------|--|
|   | 1            | 2    |  |
| Placement of Cigarette                                    | Flat         | Flat |  |
| Unsafe escalating combustion                              | No           | No   |  |
| Testing assembly consumed                                 | No           | No   |  |
| Smoulders to extremities/full thickness                   | No           | No   |  |
| Smoulders more than 1 hour                                | No           | No   |  |
| In final examination, presence of progressive smouldering | No           | No   |  |

| Flaming criteria                           | 1                 | 2                 |
|--|-------------------|-------------------|
| Occurrence of flames                       | No                | No                |
| Specimen Result (Ignition or Non-ignition) | Non-Ignition (NI) | Non-Ignition (NI) |

Any "Yes" in smouldering or flaming criteria means Ignition

# Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

## **Comments**

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.





Telephone: +44 (0) 113 259 1999 Email: info@bttg.co.uk

: <u>www.bttg.co.uk</u>

Date: 24 August 2021

Our Ref: 23/58848B/08/21 Your Ref: ---

Page: 4 of 6

Client: Gabriel A/S

## FIRE TESTS ACCORDING TO BS EN 1021-2:2014

Assessment of the ignitability of upholstered furniture. Part 2. Ignition Source 1: Match flame equivalent.

#### **Pre-Treatment**

The material received no pre-treatment as the fabric is stated not to be FR treated.

# Conditioning

The sample was conditioned for at least 16 hours at a temperature of  $23\pm2^{\circ}$ C and relative humidity of  $50\pm5\%$ .

The sample was tested in a room of volume 25m<sup>3</sup> and 20°C.

#### **Procedure**

The test was carried out in accordance with BS EN 1021-2:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 35-36 kg/m<sup>3</sup>.

Tests were made using ignition source 1.

## Requirements

The specimens shall not:-

## **Smouldering Criteria**

- a) display escalating combustion requiring active extinction.
- b) smoulders until it is essentially consumed within the test duration.
- c) smoulder to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.





Telephone: +44 (0) 113 259 1999 Email: info@bttg.co.uk

: www.bttg.co.uk

Date: 24 August 2021

Our Ref: 23/58848B/08/21 Your Ref: ---

Page: 5 of 6

Client: Gabriel A/S

# **Requirements (Continued)**

## Flaming Criteria

display escalating combustion requiring active extinction.
burns until it is essentially consumed within the test duration.
burns to the extremities of the specimen, or through the full thickness, within the duration of the test.
exhibit any flaming for more than 120 seconds after removal of the burner tube.

#### Results

|                                   | Match Flame Equivalent |       | ivalent        | Comments |  |
|-----------------------------------|------------------------|-------|----------------|----------|--|
|                                   | 1                      | 2     | 3 <sup>1</sup> |          |  |
| Smouldering Criteria (Yes/No)     |                        |       |                |          |  |
| Unsafe escalating combustion      | No                     | No    |                |          |  |
| Test assembly consumed            | No                     | No    |                |          |  |
| Smoulders to extremities          | No                     | No    |                |          |  |
| Smoulders through thickness       | No                     | No    |                |          |  |
| Smoulders more than 1 hour        | No                     | No    |                |          |  |
| In final examination, presence of | l No l No              | No.   | No No          |          |  |
| progressive smouldering           | INO                    | No No |                |          |  |
|                                   |                        |       |                |          |  |
| Ignitability Performance (Yes/No) |                        |       |                |          |  |
| Unsafe escalating combustion      | No                     | No    |                |          |  |
| Test assembly consumed            | No                     | No    |                |          |  |
| Flames to extremities             | No                     | No    |                |          |  |
| Flames through thickness          | No                     | No    |                |          |  |
| Flames longer than 120 seconds    | No                     | No    |                |          |  |
| Ignition / Non Ignition ( I/NI )  | NI                     | NI    |                |          |  |

## Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.







Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 24 August 2021

Our Ref: 23/58848B/08/21

Your Ref: ---

Page: 6 of 6

Client: Gabriel A/S

Enquiries concerning this report should be addressed to Customer Services.

# **Comments**

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-2.

The overall uncertainty budget for both BS EN 1021: Part 1 and 2:2014 is as follows:-

Timings: ±2 seconds.

Reported by:.....

**B** Bland

**Technical Customer Service Officer** 

Countersigned By:

P Doherty

Manager

